

The thickener compatibility chart below should be used as a guide to determine compatibility only. Compatibility testing is the only way to verify end product compatibility. Other factors including environment can affect the compatibility of the finished product including temperature, load and additives.

	Simple Soaps				Complex Soaps					Other	
	Al	Ca	Li	Na	Al	Ba	Ca	Li	Na	Be	Pu
Aluminium	✓	●	✓	●	✓	●	✓	✓	●	✓	✓
Calcium	●	✓	✓	✓	✓	✓	✓	●	✓	✓	✓
Lithium	✓	✓	✓	<	✓	✓	✓	✓	<	●	●
Sodium	●	✓	<	✓	✓	✓	●	●	✓	<	✓
Aluminium Complex	✓	✓	✓	✓	✓	✓	●	✓	●	●	●
Barium Complex	●	✓	✓	✓	✓	✓	●	●	✓	✓	●
Calcium Complex	✓	✓	✓	●	●	●	✓	✓	✓	●	✓
Lithium Complex	✓	●	✓	●	✓	●	✓	✓	●	✓	●
Sodium Complex	●	✓	<	✓	●	✓	✓	●	✓	<	✓
Bentonite	✓	✓	●	<	●	✓	●	✓	<	✓	✓
Polyurea	✓	✓	●	✓	●	●	✓	●	✓	✓	✓



✓ = Good  
 ● = Acceptable  
 < = Poor

The information set forth herein is furnished free of charge and is based on technical data that IKV TRIBOLOGY believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Because conditions of use are outside our control, we make no warranties, express or implied and assume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

T: 01291 691953  
 sales@ikvlubricants.com  
 www.ikvlubricants.com